



Cai Yun ® 6000 T/W

High Mesh Water-based Paste

Application

1. use 200-250 mesh count screen to do block printing, use 150-200 mesh count screen to do dot printing. Slightly lean the scraper to increase the amount of paste passing through the screen so as to enhance opacity.
2. After printing, cover the screen with paste to avoid screen blockage.
3. For block printing, flash drying on the surface is needed before printing the next color; for dot printing, wet-on-wet printing is applicable.
4. After printing, belt curing at 130-150°C for 2 - 3 minutes.

Storage

Keep container tightly closed and in a well-ventilated place. Most suitable storage temperature is 5~35°C. Keep away from heat, steam pipe or sunlight.

Further Information

The information provided is correct to the best of our knowledge, information and belief at the date of its publication. The information given is designed only as a guidance for safe handling, use, processing, storage, transport, disposal and release and is not to be considered a warranty or quality specification.